



Heriot-Watt University
Research Gateway

Nanotribology at high temperatures

Citation for published version:

Goel, S, Stukowski, A, Goel, G, Luo, X & Reuben, RL 2012, 'Nanotribology at high temperatures', *Beilstein Journal of Nanotechnology*, vol. 3, pp. 586-588. <https://doi.org/10.3762/bjnano.3.68>

Digital Object Identifier (DOI):

[10.3762/bjnano.3.68](https://doi.org/10.3762/bjnano.3.68)

Link:

[Link to publication record in Heriot-Watt Research Portal](#)

Document Version:

Publisher's PDF, also known as Version of record

Published In:

Beilstein Journal of Nanotechnology

Publisher Rights Statement:

Creative Commons by Attribution

General rights

Copyright for the publications made accessible via Heriot-Watt Research Portal is retained by the author(s) and / or other copyright owners and it is a condition of accessing these publications that users recognise and abide by the legal requirements associated with these rights.

Take down policy

Heriot-Watt University has made every reasonable effort to ensure that the content in Heriot-Watt Research Portal complies with UK legislation. If you believe that the public display of this file breaches copyright please contact open.access@hw.ac.uk providing details, and we will remove access to the work immediately and investigate your claim.

Nanotribology at high temperatures

Saurav Goel^{1,2}, Alexander Stukowski³, Gaurav Goel⁴, Xichun Luo^{*1,2,§}
and Robert L. Reuben¹

Commentary

Open Access

Address:

¹School of Engineering and Physical Sciences, Heriot-Watt University, Edinburgh, EH144AS, UK, ²School of Computing and Engineering, University of Huddersfield, Huddersfield, HD13DH, UK, ³Lawrence Livermore National Laboratory, Livermore, California, USA and ⁴School of Engineering and Technology, Sharda University, Greater Noida, 201306, India

Email:

Xichun Luo* - x.luo@hud.ac.uk

* Corresponding author

§ Tel.: +44 1484 473806, Fax: +44 1484 472161

Keywords:

CBN; diamond; high temperature

Beilstein J. Nanotechnol. **2012**, *3*, 586–588.

doi:10.3762/bjnano.3.68

Received: 01 May 2012

Accepted: 26 July 2012

Published: 15 August 2012

Associate Editor: E. Meyer

© 2012 Goel et al; licensee Beilstein-Institut.

License and terms: see end of document.

Abstract

Recent molecular dynamics simulation results have increased conceptual understanding of the grazing and the ploughing friction at elevated temperatures, particularly near the substrate's melting point. In this commentary we address a major constraint concerning its experimental verification.

Introduction

It was postulated some time ago that a component sliding under lightly loaded conditions should experience very low friction and nearly zero wear [1]. Recent research, however, has shown a steep rise in the grazing friction during wearless sliding, primarily attributed to the adhesion between the interacting surfaces [2]. A major assumption in the atomistic simulation associated with this finding was the consideration of the diamond tip as a wearless rigid body for ease of computation. Accordingly, it has been suggested [2] that the steep rise in grazing friction and the gradual drop in ploughing friction at high temperatures may affect all materials and should be pursued experimentally [3].


However, diamond is known to exhibit poor thermo-chemo-mechanical stability particularly against low carbon ferrous alloys [4] and at elevated temperatures [5]. It is surprising, but true, that diamond, the hardest material available (until the commercial realization of beta carbon nitride β -(C₃N₄) [6]), wears out rapidly when it is rubbed against low carbon ferrous alloys and pure iron [7]. A hypothesis was proposed by Paul et al. [8] ascribing the rapid chemical wear of diamond tips to the presence of unpaired d-shell electrons in the substrate. Utilizing this proposition, a research group from Bremen University, Germany, has reversed the roles of the conventionally used cutting tool and the workpiece material and has

succeeded in machining a diamond substrate using a steel rod as a tip [9].

This raises a key question concerning the stability of diamond tips during nanoscratch tests at elevated temperatures and more categorically against low carbon ferrous alloys. The wear of the diamond tip will change the contact area which will alter the frictional force as the latter depends linearly on the number of atoms that chemically interact across the surface [10]. Then, the question arises as to what other options are available for a tool tip for nanotribological applications at elevated temperatures, if not diamond. We attempt to answer this question below.

Discussion

Principally, ultra-hard materials – materials whose hardness is attributable to covalent bonding – can be represented using the “composition cycle” shown in Figure 1. This cycle involves the four elements carbon (C), boron (B), silicon (Si) and nitrogen (N). The combination of any two chemical species from this composition cycle produces a compound exhibiting ultra-high hardness, e.g., CBN, SiC, Si₃N₄, B₄C and the recently recognized C₃N₄.



Under ambient conditions – while nitrogen reside in a gaseous form as individual chemical species – boron, silicon and diamond are known to prefer a solid state. Due to its abundance and its capability to form better oxides, silicon dominated the electronic consumer market [12] while the ubiquitous use of diamond originates from its unique features such as high thermal conductivity, high wear resistance and its ability to form extremely sharp cutting edges [13]. Moreover, both

diamond and silicon are known to be hard and brittle [14,15] in their sp³-bonded state. Two commercially available materials from this composition cycle, diamond (C) and cubic boron nitride (CBN), possess ultra-high hardness (attributed both to sp³-bonding and relatively short bond lengths) and, for this reason, they are frequently used to manufacture cutting tips. While diamond resides in a cubic lattice structure, CBN possesses a zinc-blende structure having boron atoms at the crystal site (0,0,0) and nitrogen atoms in the respective centers of the boron tetrahedra. Although, a chemical bond between the carbon atoms in diamond is stronger than the corresponding isoelectronic bond between nitrogen and boron atoms, we propose that cubic boron nitride “CBN” could be an alternative appropriate choice for high-temperature nanotribology applications because of its superior thermal and chemical stability compared to that of diamond. Even though diamond and CBN have similar lattice structures, their surface chemistry is different. In a CBN lattice, boron atoms have only three valence electrons on the surface while nitrogen atoms have five. However, two of these five electrons of nitrogen can form a stable pair, leaving three valence electrons to bond with boron. On the contrary, a diamond lattice has four valence electrons; therefore, only a maximum of three electrons on the surface can have stable bonding between them. Consequently, this leads to the possibility that the remaining one or two electrons of each surface atom in diamond react readily with other materials like iron, nickel and even silicon [16] in a tribological environment. This seems to be a plausible reason why CBN was found as an efficient cutting tip to machine ferrous alloys [17] and silicon [18] in comparison to a diamond tip. Hence, in contrast to diamond, CBN has fewer dangling bonds on the surface which makes it more inert.

Conclusion

It is proposed that the results for the ploughing friction and grazing friction in a high temperature environment must be retested using a CBN probe to reconfirm the state-of-the-art knowledge. Moreover, the influence of the rake angle of the tip must necessarily be accounted for when generalizing the results of grazing friction, as it is an integral part in governing atomic scale friction [19,20].

Acknowledgements

The authors would like to thank Luke Mason (PhD student) from Heriot-Watt University, UK, for his constructive suggestions during the proofreading stage. This work is part of a PhD project which was funded through Scottish Overseas Research Students Award (with additional funding from the Neilson fund) from the School of Engineering and Physical Sciences of Heriot-Watt University to which the first author (SG) is always indebted.

References

- Bhushan, B.; Israelachvili, J. N.; Landman, U. *Nature* **1994**, *374*, 607–616. doi:10.1038/374607a0
- Zykova-Timan, T.; Ceresoli, D.; Tosatti, E. *Nat. Mater.* **2007**, *6*, 230–234. doi:10.1038/nmat1836
- Sandhu, A. *Nat. Nanotechnol.* **2007**, *2*. doi:10.1038/nnano.2007.59
- Komanduri, R.; Shaw, M. C. *Nature* **1975**, *255*, 211–213. doi:10.1038/255211a0
- Koskiliina, J. Quantum Chemical Studies on Atomic-scale Tribology of Diamond and Boron Nitride. Ph.D. Thesis, University of Joensuu, Joensuu, Finland, 2007.
- Wu, M. L.; Gruz, M. U.; Dravid, V. P.; Chung, Y. W.; Anders, S.; Freire, F. L.; Mariotto, G. *Appl. Phys. Lett.* **2000**, *76*, 2692–2694. doi:10.1063/1.126743
- Narulkar, R. Investigations on the mechanism of wear of single crystal diamond tool in nanometric cutting of iron using molecular dynamics and the development of generalised potential energy surfaces (GPES) based on ab initio calculations. Ph.D. Thesis, Oklahoma State University, Oklahoma, USA, 2009.
- Paul, E.; Evans, C. J.; Mangamelli, A.; McGlauffin, M. L.; Polvani, R. S. *Precis. Eng.* **1996**, *18*, 4–19. doi:10.1016/0141-6359(95)00019-4
- Brinksmeier, E.; Riemer, O.; Robert, C. Friction polishing and contact tests of diamond by solid metals, P7.21.. In *Proceedings of the 12th euspen International Conference, Vol. 2*, Stockholm, Sweden, June 4–8, 2012; euspen: Bedford, UK, 2012; pp 452–455.
- Mo, Y.; Turner, K. T.; Szlufarska, I. *Nature* **2009**, *457*, 1116–1119. doi:10.1038/nature07748
- Shaw, M. C. In *Metal Cutting Principles*, 2nd ed.; Crookall, J. R.; Shaw, M. C.; Suh, N. P., Eds.; Oxford Series on Advanced Manufacturing, Vol. 5; Oxford University Press: New York, 2005.
- Segal, M. *Nature* **2012**, *483*, S43–S44. doi:10.1038/483S43a
- Narulkar, R.; Bukkapatnam, S.; Raff, L. M.; Komanduri, R. *Comput. Mater. Sci.* **2009**, *45*, 358–366. doi:10.1016/j.commatsci.2008.10.007
- Gilman, J. J. *Science* **1993**, *261*, 1436–1439. doi:10.1126/science.261.5127.1436
- Mélinon, P.; Masenelli, B.; Tournus, F.; Perez, A. *Nat. Mater.* **2007**, *6*, 479–490. doi:10.1038/nmat1914
- Goel, S.; Luo, X.; Reuben, R. L. *Tribol. Int.*, in press. doi:10.1016/j.triboint.2012.06.027
- Tönshoff, H. K.; Arendt, C.; Amor, R. B. *CIRP Ann.* **2000**, *49*, 547–566. doi:10.1016/S0007-8506(07)63455-6
- Goel, S.; Luo, X.; Reuben, R. L.; Bin Rashid, W. *Mater. Lett.* **2012**, *68*, 507–509. doi:10.1016/j.matlet.2011.11.028
- Samuels, L. E. *Sci. Am.* **1978**, *239*, 132–152. doi:10.1038/scientificamerican1178-132
- Komanduri, R.; Chandrasekaran, N.; Raff, L. M. *Phys. Rev. B* **2000**, *61*, 14007–14019. doi:10.1103/PhysRevB.61.14007

License and Terms

This is an Open Access article under the terms of the Creative Commons Attribution License (<http://creativecommons.org/licenses/by/2.0>), which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

The license is subject to the *Beilstein Journal of Nanotechnology* terms and conditions: (<http://www.beilstein-journals.org/bjnano>)

The definitive version of this article is the electronic one which can be found at: [doi:10.3762/bjnano.3.68](https://doi.org/10.3762/bjnano.3.68)